













Technical Data Sheet

Metropolis Series
Pittsburgh Plant



Product Name	Swatch	Size	Standard	Durability Class (Grade)	Dimensional Variation (Type)	Compressive Strength (psi)	24-hr Cold Water Absorption (%)	5-hr Boil Absorption (%)	IRA (g/min per 30in ²)	Core Volume (%)
Blacktone Matt		Modular	ASTM C216	SW	FBX	>5,000	<6	<10	<20	<25
Brookhaven		Modular	ASTM C216	SW	FBX	>5,000	<6	<10	<20	<25
Courtland Matt		Modular	ASTM C216	SW	FBX	>5,000	<6	<10	<20	<25
Genesee Matt		Modular	ASTM C216	SW	FBX	>5,000	<6	<10	<20	<25
Harding Blend Redburn		Modular	ASTM C216	SW	FBX	>5,000	<6	<10	<20	<25
Khaki Matt		Modular	ASTM C216	SW	FBX	>10,000	<6	<10	<10	<25
Light Buff Matt		Modular	ASTM C216	SW	FBX	>5,000	<6	<10	<10	<25
Richmond		Modular	ASTM C216	SW	FBX	>5,000	<6	<10	<20	<25
Spring Hue Matt		Modular	ASTM C216	SW	FBX	>15,000	<6	<10	<10	<25
Tangerine Matt		Modular	ASTM C216	SW	FBX	>15,000	<6	<10	<10	<25
Whitehall		Modular	ASTM C216	SW	FBX	>5,000	<6	<10	<10	<25
Wingate		Modular	ASTM C216	SW	FBX	>5,000	<6	<10	<20	<25

This data represents average results. If specific test results are required, sample should be taken from current production lots. U.S. STANDARD TEST METHODS (ASTM C67) ARE USED AS APPLICABLE, UNLESS OTHERWISE NOTED. ©2024

Size	Width	Height	Length	Weight	Brick per Cube	Brick per Sq Ft
Modular	3-9/16"	2-1/4"	7-5/8"	4.1	525	6.86