

Technical Data Sheet

San Selmo Corso Series
International (Italy)



| Product Name | Swatch | Size | Standard | Durability Class (Grade) | Dimensional Variation (Type) | Compressive Strength (psi) | 24-hr Cold Water Absorption (%) | 5-hr Boil Absorption (%) | IRA (g/min per 30in ²) | Core Volume (%) |
|--------------|---|-------|-----------|--------------------------|------------------------------|----------------------------|--|--------------------------|------------------------------------|-----------------|
| Adda Raw |  | Corso | ASTM C216 | SW | FBA | >3,000 | Passes ASTM 50-Cycle Freeze/Thaw Testing | <65 | uncored | |
| Arno Raw |  | Corso | ASTM C216 | SW | FBA | >3,000 | Passes ASTM 50-Cycle Freeze/Thaw Testing | <65 | uncored | |
| Brenta Raw |  | Corso | ASTM C216 | SW | FBA | >3,000 | Passes ASTM 50-Cycle Freeze/Thaw Testing | <65 | uncored | |
| Livenza Raw |  | Corso | ASTM C216 | SW | FBA | >3,000 | Passes ASTM 50-Cycle Freeze/Thaw Testing | <65 | uncored | |
| Piave Raw |  | Corso | ASTM C216 | SW | FBA | >3,000 | Passes ASTM 50-Cycle Freeze/Thaw Testing | <65 | uncored | |
| Potenza Raw |  | Corso | ASTM C216 | SW | FBA | >3,000 | Passes ASTM 50-Cycle Freeze/Thaw Testing | <65 | uncored | |
| Reno Raw |  | Corso | ASTM C216 | SW | FBA | >3,000 | Passes ASTM 50-Cycle Freeze/Thaw Testing | <65 | uncored | |

This data represents average results. If specific test results are required, sample should be taken from current production lots. U.S. STANDARD TEST METHODS (ASTM C67) ARE USED AS APPLICABLE, UNLESS OTHERWISE NOTED. ©2024

| Size | Width | Height | Length | Weight | Brick per Pallet | Brick per Sq Ft |
|-------|----------|---------|-----------|--------|------------------|-----------------|
| Corso | 3-15/16" | 1-9/16" | 19-11/16" | 8.1 | 137 | 3.7 |