Technical Data Sheet

Designer Klaycoat® Series

Hanley Plant



| Product Name | Swatch | Size | Standard | Durability Class (Grade) | Dimensional Variation (Type) | Compressive Strength (psi) | 24-hr Cold Water Absorption (%) | 5-hr Boil Absorption (%) | IRA (g/min per 30in ²) | Core Volume (%) |
|----------------------|--------|---------|-----------|--------------------------------|------------------------------------|----------------------------------|--|--------------------------------|--|--------------------|
| Charcoal Klaycoat | | Modular | ASTM C216 | SW | FBX | >10,000 | <6 | <10 | <10 | <25 |
| Khaki Stone Klaycoat | | Modular | ASTM C216 | sw | FBX | >10,000 | <6 | <10 | <10 | <25 |
| Stone Grey Klaycoat | | Modular | ASTM C216 | sw | FBX | >10,000 | <6 | <10 | <10 | <25 |
| Urban Grey Klaycoat | | Modular | ASTM C216 | sw | FBX | >10,000 | <6 | <10 | <10 | <25 |

This data represents average results. If specific test results are required, sample should be taken from current production lots. U.S. STANDARD TEST METHODS (ASTM C67) ARE USED AS APPLICABLE, UNLESS OTHERWISE NOTED. ©2024

| Size | Width | Height | Length | Weight | Brick per Cube | Brick per Sq Ft | | | |
|---|--------|--------|--------|--------|-------------------|--------------------|--|--|--|
| Modular | 3-5/8" | 2-1/4" | 7-5/8" | 4.0 | 525 | 6.86 | | | |
| Note: Products are also available as Thin Brick, see Thin Brick Technical Data Sheet. | | | | | | | | | |

Technical Data Sheet

Designer Klaycoat® Series -- Thin Brick Hanley Plant



| Product Name | Swatch | Size | Standard | Durability Class (Grade) | Dimensional Variation (Type) | Compressive Strength (psi) | 24-hr Cold Water Absorption (%) | 5-hr Boil Absorption (%) | IRA (g/min per 30in²) | Core Volume (%) |
|------------------------------------|--------|---------|------------|--------------------------------|------------------------------------|----------------------------------|--|--------------------------------|-----------------------------|--------------------|
| Charcoal Klaycoat Thin Brick | | Modular | ASTM C1088 | Exterior | твх | N/A | <6 | <10 | N/A | N/A |
| Khaki Stone Klaycoat Thin Brick | | Modular | ASTM C1088 | Exterior | твх | N/A | <6 | <10 | N/A | N/A |
| Stone Grey Klaycoat Thin Brick | | Modular | ASTM C1088 | Exterior | твх | N/A | <6 | <10 | N/A | N/A |
| Urban Grey Klaycoat Thin Brick | | Modular | ASTM C1088 | Exterior | твх | N/A | <6 | <10 | N/A | N/A |

This data represents average results. If specific test results are required, sample should be taken from current production lots. U.S. STANDARD TEST METHODS (ASTM C67) ARE USED AS APPLICABLE, UNLESS OTHERWISE NOTED. ©2024

| Size | Thickness | Width | Height | Length | Weight | Brick per Pallet | Brick per Sq Ft | | |
|---|-----------|--------|--------|--------|--------|---------------------|--------------------|--|--|
| Modular Thin Brick Flat | 1/2" | 1/2" | 2-1/4" | 7-5/8" | 0.8 | 3840 | 6.86 | | |
| Modular Thin Brick Corner | 1/2" | 3-5/8" | 2-1/4" | 7-5/8" | 1.1 | 2100 | 4.5/LF | | |
| Note: Products are also available as Full Brick, see Full Brick Technical Data Sheet. | | | | | | | | | |