

Technical Data Sheet



Product Range	Product Name	Illustration	Swatch	Length (in)	Width (in)	Height (in)	Standard	Durability Class (Grade)	Dimensional Variation (Type)	Average Unit Wt. (lb.)	Units per Square Foot	Pack Size	Compressive Strength (psi)	24-hr Cold Water Absorption (%)	5-hr Boil Absorption (%)	IRA (g/min per 30in ²)	Core Volume (%)
S.Anselmo Corso	Arno Raw			19-11/16	3-15/16	1-9/16	ASTM C216	SW	FBA	8.0	3.7	137	>15,000	<6	<10	<10	uncored
S.Anselmo Corso	Arno Textured			19-11/16	3-15/16	1-9/16	ASTM C216	SW	FBA	7.0	3.7	137	>5,000	<14	<17	<49	uncored
S.Anselmo Corso	Brenta Raw			19-11/16	3-15/16	1-9/16	ASTM C216	SW	FBA	8.0	3.7	137	>15,000	<6	<10	<10	uncored
S.Anselmo Corso	Livenza Raw			19-11/16	3-15/16	1-9/16	ASTM C216	SW	FBA	8.0	3.7	137	>15,000	<6	<10	<10	uncored
S.Anselmo Corso	Marana Raw			19-11/16	3-15/16	1-9/16	ASTM C216	SW	FBA	8.0	3.7	137	>15,000	<6	<10	<10	uncored
S.Anselmo Corso	Marana Textured			19-11/16	3-15/16	1-9/16	ASTM C216	SW	FBA	7.0	3.7	137	>5,000	<14	<17	<40	uncored
S.Anselmo Corso	Piave Raw			19-11/16	3-15/16	1-9/16	ASTM C216	SW	FBA	8.0	3.7	137	>15,000	<6	<10	<10	uncored
S.Anselmo Corso	Piave Textured			19-11/16	3-15/16	1-9/16	ASTM C216	SW	FBA	7.0	3.7	137	>5,000	<14	<17	<40	uncored
S.Anselmo Corso	Potenza Raw			19-11/16	3-15/16	1-9/16	ASTM C216	SW	FBA	8.0	3.7	137	>5,000	<14	<17	<20	uncored
S.Anselmo Corso	Potenza Textured			19-11/16	3-15/16	1-9/16	ASTM C216	SW	FBA	7.0	3.7	137	>5,000	<14	<17	<49	uncored

This data represents average results. If specific test results are required, sample should be taken from current production lots. U.S. STANDARD TEST METHODS (ASTM C67) ARE USED AS APPLICABLE, UNLESS OTHERWISE NOTED.