## **Technical Data Sheet**

## **Chateau Series**

Marseilles Plant



Product Name	Swatch	Size	Stan dard	Durability Class (Grade)	Dimensional Variation (Type)	Compressive Strength (psi)	24-hr Cold Water Absorption (%)	5-hr Boil Absorption (%)	IRA (g/min per 30in <sup>2</sup> )	Core Volume (%)
Bordeaux		Modular	ASTM C652	SW	HBS	>5,000	<8	<10	<20	<40
bolueaux		Econo	ASTM C652	SW	HBS	>5,000	<8	<10	<20	<40
Cedar Creek		Modular	ASTM C652	sw	HBS	>5,000	<8	<10	<20	<40
Cedar Creek		Econo	ASTM C652	SW	HBS	>5,000	<8	<10	<20	<40
Colonial Rose		Modular	ASTM C652	SW	HBS	>5,000	<8	<10	<20	<40
Colonial Rose		Econo	ASTM C652	SW	HBS	>5,000	<8	<10	<20	<40
Lare do	William of the last of the las	Modular	ASTM C652	SW	HBS	>5,000	<8	<10	<20	<40
Laieuo	W 1 1 1 1 1 1 1 1 1 1 1 1 1 1 1 1 1 1 1	Econo	ASTM C652	SW	HBS	>5,000	<8	<10	<20	<40
London Mist		Modular	ASTM C652	SW	HBS	>5,000	<8	<10	<20	<40
London Wilst	THE PERSON NAMED IN	Econo	ASTM C652	SW	HBS	>5,000	<8	<10	<20	<40
Morning Dove		Modular	ASTM C652	sw	HBS	>5,000	<8	<10	<20	<40
Woming Bove		Econo	ASTM C652	sw	HBS	>5,000	<8	<10	<20	<40
St. Thomas	THE RESEARCH	Modular	ASTM C652	sw	HBS	>5,000	<8	<10	<20	<40
ou momus	10 To 10	Econo	ASTM C652	SW	HBS	>5,000	<8	<10	<20	<40
Wheaton	11)	Modular	ASTM C652	sw	HBS	>5,000	<8	<10	<20	<40
wireacon	10.000	Econo	ASTM C652	sw	HBS	>5,000	<8	<10	<20	<40
Yukon Winter		Modular	ASTM C652	sw	HBS	>5,000	<8	<10	<20	<40
Tunon Time!	Mark The Land	Econo	ASTM C652	SW	HBS	>5,000	<8	<10	<20	<40

This data represents average results. If specific test results are required, sample should be taken from current production lots. U.S. STANDARD TEST METHODS (ASTM C67) ARE USED AS APPLICABLE, UNLESS OTHERWISE NOTED.

Size	Width	Height	Length	Weight	Brick per Cube	Brick per Sq Ft
Modular	3-5/8"	2-1/4"	7-5/8"	3.5	530	6.86
Econo	3-5/8"	3-5/8"	7-5/8"	5.8	330	4.50