

! "#\$%&#'()\*'+), \$""+  
**Craftsman Series**  
 !"#&'()\*



Product Name	Swatch	Size	Standard	Durability Class (Grade)	Dimensional Variation (Type)	Compressive Strength (psi)	24-hr Cold Water Absorption (%)	5-hr Boil Absorption (%)	IRA (g/min per 30in <sup>1</sup> )	Core Volume (%)
Antique Ivory		Overize	ASTM C216	SW	FBA	>3,000	<14	<17	<48	uncored
Atlanta		Overize	ASTM C216	SW	FBA	>3,000	<14	<17	<48	uncored
Avignon		Overize	ASTM C216	SW	FBA	>3,000	<14	<17	<48	uncored
Barlow		Overize	ASTM C216	SW	FBA	>3,000	<14	<17	<48	uncored
Belgium		Overize	ASTM C216	SW	FBA	>3,000	<14	<17	<48	uncored
Brandywine		Overize	ASTM C216	SW	FBA	>3,000	<14	<17	<48	uncored
Cherry Lane		Overize	ASTM C216	SW	FBA	>3,000	<14	<17	<48	uncored
Donohue		Overize	ASTM C216	SW	FBA	>3,000	<14	<17	<48	uncored
French Provincial		Overize	ASTM C216	SW	FBA	>3,000	<14	<17	<48	uncored
Georgian		Overize	ASTM C216	SW	FBA	>3,000	<14	<17	<48	uncored
Lorraine Full Range		Overize	ASTM C216	SW	FBA	>3,000	<14	<17	<48	uncored
Monticello		Overize	ASTM C216	SW	FBA	>3,000	<14	<17	<48	uncored
Old Savannah		Overize	ASTM C216	SW	FBA	>3,000	<14	<17	<48	uncored
Rockdale		Overize	ASTM C216	SW	FBA	>3,000	<14	<17	<48	uncored
Rose Full Range		Overize	ASTM C216	SW	FBA	>3,000	<14	<17	<48	uncored
Royal Essex		Overize	ASTM C216	SW	FBA	>3,000	<14	<17	<48	uncored
Sahara		Overize	ASTM C216	SW	FBA	>3,000	<14	<17	<48	uncored
Scotch Tradition		Overize	ASTM C216	SW	FBA	>3,000	<14	<17	<48	uncored
Shenandoah		Overize	ASTM C216	SW	FBA	>3,000	<14	<17	<48	uncored
Trevanion		Overize	ASTM C216	SW	FBA	>3,000	<14	<17	<48	uncored
Victorian		Overize	ASTM C216	SW	FBA	>3,000	<14	<17	<48	uncored
Virginia Blend		Overize	ASTM C216	SW	FBA	>3,000	<14	<17	<48	uncored

! "#\$%&'()\*'+), \$""+  
 ; 1<?@?# A<1%BA! CD?<=<! B\*FGHI%=@A% <A?%=<%-JJKF=LKA6% >KA<<1D! CA@M2<A%>D! A?!

Size	Width	Height	Length	Weight	Brick per Cube	Brick per Sq Ft
Handmade Overize	4"	2-3/4"	8-1/2"	6.4	385	5.2

Note: products are also available as Thin Brick, see Thin Brick Technical Data Sheet.

