Technical Data Sheet

Developer Series

Iberia Plant



| Product Name | Swatch | Size | Standard | Durability Class (Grade) | Dimensional Variation (Type) | Compressive Strength (psi) | 24-hr Cold Water Absorption (%) | 5-hr Boil Absorption (%) | IRA (g/min per 30in ²) | Core Volume (%) |
|--------------|--------|-------|-----------|--------------------------------|------------------------------------|----------------------------------|--|--------------------------------|--|--------------------|
| Elyria | | Queen | ASTM C652 | SW | HBS | >5,000 | <6 | <10 | <20 | <40 |
| Grey Ash | | Queen | ASTM C652 | sw | HBS | >5,000 | <6 | <10 | <20 | <40 |
| Mentor | | Queen | ASTM C652 | sw | HBS | >5,000 | <6 | <10 | ⊘ 20 | <40 |

This data represents average results. If specific test results are required, sample should be taken from current production lots. U.S. STANDARD TEST METHODS (ASTM C67) ARE USED AS APPLICABLE, UNLESS OTHERWISE NOTED.

| Size | Width | Height | Length | Weight | Brick per Cube | Brick per Sq Ft |
|-------|-------|--------|--------|--------|-------------------|-----------------|
| Queen | 3" | 2-3/4" | 7-5/8" | 3.9 | 520 | 5.76 |