

Technical Data Sheet

Feldhaus Series – Thin Brick
International (Germany)



Product Name	Swatch	Size	Standard	Durability Class (Grade)	Dimensional Variation (Type)	Compressive Strength (psi)	24-hr Cold Water Absorption (%)	5-hr Boil Absorption (%)	IRA (g/min per 30in ²)	Core Volume (%)
100 Classic Cream Smooth		Modular	ASTM C1088	Exterior	TBX	N/A	<6	<10	N/A	N/A
313 Red Flashed Velour		Modular	ASTM C1088	Exterior	TBX	N/A	<6	<10	N/A	N/A
387 Rustic Red Flashed		Modular	ASTM C1088	Exterior	TBX	N/A	<6	<10	N/A	N/A
400 Classic Red Smooth		Modular	ASTM C1088	Exterior	TBX	N/A	<6	<10	N/A	N/A
401 Classic Red Velour		Modular	ASTM C1088	Exterior	TBX	N/A	<6	<10	N/A	N/A
511 Onyx Smooth		Modular	ASTM C1088	Exterior	TBX	N/A	<6	<10	N/A	N/A
567 Coal Brindle Smooth		Modular	ASTM C1088	Exterior	TBX	N/A	<6	<10	N/A	N/A
664 Deep Wine Handform		Modular	ASTM C1088	Exterior	TBX	N/A	<6	<10	N/A	N/A
700 Anthracite Smooth		Modular	ASTM C1088	Exterior	TBX	N/A	<6	<10	N/A	N/A
714 Sundown Flashed		Modular	ASTM C1088	Exterior	TBX	N/A	<6	<10	N/A	N/A
737 Plowed Earth Waterstruck		Modular	ASTM C1088	Exterior	TBX	N/A	<6	<10	N/A	N/A
757 Cream Waterstruck		Modular	ASTM C1088	Exterior	TBX	N/A	<6	<10	N/A	N/A
764 Gray White Waterstruck		Modular	ASTM C1088	Exterior	TBX	N/A	<6	<10	N/A	N/A
773 Rustic Gray Waterstruck		Modular	ASTM C1088	Exterior	TBX	N/A	<6	<10	N/A	N/A
777 Onyx Waterstruck		Modular	ASTM C1088	Exterior	TBX	N/A	<6	<10	N/A	N/A
800 Classic Gray Smooth		Modular	ASTM C1088	Exterior	TBX	N/A	<6	<10	N/A	N/A

This data represents average results. If specific test results are required, sample should be taken from current production lots. U.S. STANDARD TEST METHODS (ASTM C67) ARE USED AS APPLICABLE, UNLESS OTHERWISE NOTED.

Size	Thickness	Width	Height	Length	Weight	Brick per Pack	Brick per Sq Ft
Modular Thin Brick Flat	9/16"	9/16"	2-1/4"	7-5/8"	0.8	38	6.86
Modular Thin Brick Corner	9/16"	3-5/8"	2-1/4"	7-5/8"	1.2	12	4.5/LF