

# Technical Data Sheet

Galleria Glazed Series

Hanley Plant



Product Name	Swatch	Size	Standard	Durability Class (Grade)	Dimensional Variation (Type)	Compressive Strength (psi)	24-hr Cold Water Absorption (%)	5-hr Boil Absorption (%)	IRA (g/min per 30in <sup>2</sup> )	Core Volume (%)
Apricot Rose		All Sizes Special Order	ASTM C1405	Exterior	S	>10,000	<6	<10	<10	<25
Emerald		All Sizes Special Order	ASTM C1405	Exterior	S	>10,000	<6	<10	<10	<25
Ginger		All Sizes Special Order	ASTM C1405	Exterior	S	>10,000	<6	<10	<10	<25
Golden Dawn w/Clear Glaze		All Sizes Special Order	ASTM C216	SW	FBX	>10,000	<6	<10	<10	<25
Iced Grey		All Sizes Special Order	ASTM C1405	Exterior	S	>10,000	<6	<10	<10	<25
Light Grey w/ Speck		All Sizes Special Order	ASTM C1405	Exterior	S	>10,000	<6	<10	<10	<25
Metorite		All Sizes Special Order	ASTM C1405	Exterior	S	>10,000	<6	<10	<10	<25
Mustard		All Sizes Special Order	ASTM C1405	Exterior	S	>10,000	<6	<10	<10	<25
Oyster White w/ Speck		All Sizes Special Order	ASTM C1405	Exterior	S	>10,000	<6	<10	<10	<25
Pewter		All Sizes Special Order	ASTM C1405	Exterior	S	>10,000	<6	<10	<10	<25
Ruby		All Sizes Special Order	ASTM C1405	Exterior	S	>10,000	<6	<10	<10	<25
Shadow Black		All Sizes Special Order	ASTM C1405	Exterior	S	>10,000	<6	<10	<10	<25
Spice White		All Sizes Special Order	ASTM C1405	Exterior	S	>10,000	<6	<10	<10	<25
Violet		All Sizes Special Order	ASTM C1405	Exterior	S	>10,000	<6	<10	<10	<25

This data represents average results. If specific test results are required, sample should be taken from current production lots. U.S. STANDARD TEST METHODS (ASTM C67) ARE USED AS APPLICABLE, UNLESS OTHERWISE NOTED.

Size	Width	Height	Length	Weight	Brick per Cube	Brick per Sq Ft
Modular	3-5/8"	2-1/4"	7-5/8"	4.0	525	6.86
Standard	3-5/8"	2-1/4"	8"	4.3	525	6.55
Engineer	3-5/8"	2-3/4"	7-5/8"	5.0	425	5.76
Engineer Standard	3-5/8"	2-3/4"	8"	5.2	425	5.50
Norman	3-5/8"	2-1/4"	11-5/8"	6.3	315	4.57
Econo	3-5/8"	3-5/8"	7-5/8"	6.5	330	4.50
Utility	3-5/8"	3-5/8"	11-5/8"	10.1	198	3.00