

Technical Data Sheet

Hometown Series
Iberia Plant



| Product Name | Swatch | Size | Standard | Durability Class (Grade) | Dimensional Variation (Type) | Compressive Strength (psi) | 24-hr Cold Water Absorption (%) | 5-hr Boil Absorption (%) | IRA (g/min per 30in ²) | Core Volume (%) |
|--------------|---|---------|-----------|--------------------------|------------------------------|----------------------------|---------------------------------|--------------------------|------------------------------------|-----------------|
| Albany |  | Modular | ASTM C216 | SW | FBS | >3,000 | <6 | <10 | <30 | uncored |
| Augusta |  | Modular | ASTM C216 | SW | FBS | >3,000 | <6 | <10 | <30 | uncored |
| Canton |  | Modular | ASTM C216 | SW | FBS | >3,000 | <6 | <10 | <30 | uncored |
| Covington |  | Modular | ASTM C216 | SW | FBS | >3,000 | <6 | <10 | <30 | uncored |
| Jamestown |  | Modular | ASTM C216 | SW | FBS | >3,000 | <6 | <10 | <30 | uncored |
| Windham |  | Modular | ASTM C216 | SW | FBS | >3,000 | <6 | <10 | <30 | uncored |

This data represents average results. If specific test results are required, sample should be taken from current production lots. U.S. STANDARD TEST METHODS (ASTM C67) ARE USED AS APPLICABLE, UNLESS OTHERWISE NOTED.

| Size | Width | Height | Length | Weight | Brick per Cube | Brick per Sq Ft |
|---------|--------|--------|--------|--------|----------------|-----------------|
| Modular | 3-1/2" | 2-1/4" | 7-5/8" | 4.7 | 525 | 6.86 |