Technical Data Sheet

Urban Crème Velour Series

Sergeant Bluff Plant



| Product Name | Swatch | Size | Stan dard | Durability Class (Grade) | Dimensional Variation (Type) | Compressive Strength (psi) | 24-hr Cold Water Absorption (%) | 5-hr Boil Absorption (%) | IRA (g/min per 30in ²) | Core Volume (%) |
|-----------------------|--------|---------|-----------|--------------------------------|------------------------------------|----------------------------------|--|--------------------------------|--|--------------------|
| Buttemut Velour | | Modular | ASTM C216 | sw | FBX | >10,000 | <6 | <10 | <10 | <25 |
| butterriut verour | | Utility | ASTM C216 | SW | FBX | >10,000 | <6 | <10 | <10 | <25 |
| Clear Buff Velour | | Modular | ASTM C216 | SW | FBX | >10,000 | <6 | <10 | <10 | <25 |
| Clear Bull Velour | | Utility | ASTM C216 | sw | FBX | >10,000 | <6 | <10 | <10 | <25 |
| Desert Blend Velour | | Modular | ASTM C216 | sw | FBX | >10,000 | <6 | <10 | <10 | <25 |
| besett blend velour | | Utility | ASTM C216 | SW | FBX | >10,000 | <6 | <10 | <10 | <25 |
| Grand Canyon Velour | | Modular | ASTM C216 | sw | FBX | >10,000 | <6 | <10 | <10 | <25 |
| Giana Canyon Veloui | | Utility | ASTM C216 | sw | FBX | >10,000 | <6 | <10 | <10 | <25 |
| Prairie Sunset Velour | | Modular | ASTM C216 | SW | FBX | >10,000 | <6 | <10 | <10 | <25 |
| Traine Sunset verour | | Utility | ASTM C216 | SW | FBX | >10,000 | <6 | <10 | <10 | <25 |
| Regency Blend Velour | | Modular | ASTM C216 | sw | FBX | >10,000 | <6 | <10 | <10 | <25 |
| Regency Diena Veloui | | Utility | ASTM C216 | SW | FBX | >10,000 | <6 | <10 | <10 | <25 |

This data represents average results. If specific test results are required, sample should be taken from current production lots. U.S. STANDARD TEST METHODS (ASTM C67) ARE USED AS APPLICABLE, UNLESS OTHERWISE NOTED.

| Size | Width | Height | Length | Weight | Brick per Cube | Brick per Sq Ft |
|---------|--------|--------|---------|--------|-------------------|-----------------|
| Modular | 3-5/8" | 2-1/4" | 7-5/8" | 3.8 | 525 | 6.86 |
| Utility | 3-5/8" | 3-5/8" | 11-5/8" | 9.1 | 201 | 3.00 |