

Technical Data Sheet

Urban Gray Velour Series
Sergeant Bluff Plant



Product Name	Swatch	Size	Standard	Durability Class (Grade)	Dimensional Variation (Type)	Compressive Strength (psi)	24-hr Cold Water Absorption (%)	5-hr Boil Absorption (%)	IRA (g/min per 30in ²)	Core Volume (%)
Beige Gray Velour		Modular	ASTM C216	SW	FBX	>10,000	<6	<10	<10	<25
		Utility	ASTM C216	SW	FBX	>10,000	<6	<10	<10	<25
Castile Gray Velour		Modular	ASTM C216	SW	FBS	>10,000	<6	<10	<10	<25
		Utility	ASTM C216	SW	FBS	>10,000	<6	<10	<10	<25
Charcoal Gray Velour		Modular	ASTM C216	SW	FBX	>10,000	<6	<10	<10	<25
		Utility	ASTM C216	SW	FBX	>10,000	<6	<10	<10	<25
Dunes Gray Velour		Modular	ASTM C216	SW	FBX	>10,000	<6	<10	<10	<25
		Utility	ASTM C216	SW	FBX	>10,000	<6	<10	<10	<25
Oxford Gray Velour		Modular	ASTM C216	SW	FBX	>10,000	<6	<10	<10	<25
		Utility	ASTM C216	SW	FBX	>10,000	<6	<10	<10	<25
Stonington Gray Velour		Modular	ASTM C216	SW	FBX	>10,000	<6	<10	<10	<25
		Utility	ASTM C216	SW	FBX	>10,000	<6	<10	<10	<25
White Plains Velour		Modular	ASTM C216	SW	FBX	>10,000	<6	<10	<10	<25
		Utility	ASTM C216	SW	FBX	>10,000	<6	<10	<10	<25

This data represents average results. If specific test results are required, sample should be taken from current production lots. U.S. STANDARD TEST METHODS (ASTM C67) ARE USED AS APPLICABLE, UNLESS OTHERWISE NOTED.

Size	Width	Height	Length	Weight	Brick per Cube	Brick per Sq Ft
Modular	3-5/8"	2-1/4"	7-5/8"	3.8	525	6.86
Utility	3-5/8"	3-5/8"	11-5/8"	9.1	201	3.00