

# Technical Data Sheet

Williamsburg Series

Adel Plant



Product Name	Swatch	Size	Standard	Durability Class (Grade)	Dimensional Variation (Type)	Compressive Strength (psi)	24-hr Cold Water Absorption (%)	5-hr Boil Absorption (%)	IRA (g/min per 30in <sup>2</sup> )	Core Volume (%)
Birchwood Williamsburg		Builders Special	ASTM C652	SW	HBA	>10,000	<6	<10	<10	<40
Black Williamsburg		Builders Special	ASTM C652	SW	HBA	>10,000	<6	<10	<10	<40
Bradford Williamsburg		Builders Special	ASTM C652	SW	HBA	>10,000	<6	<10	<10	<40
Buckingham Williamsburg		Builders Special	ASTM C652	SW	HBA	>10,000	<6	<10	<10	<40
Cherry Creek Williamsburg		Builders Special	ASTM C652	SW	HBA	>10,000	<6	<10	<10	<40
Hampton Williamsburg		Builders Special	ASTM C652	SW	HBA	>10,000	<6	<10	<10	<40
Millstone Williamsburg		Builders Special	ASTM C652	SW	HBA	>10,000	<6	<10	<10	<40
Old Heritage Williamsburg		Builders Special	ASTM C652	SW	HBA	>15,000	<6	<10	<10	<40
Saddle Brown Williamsburg		Builders Special	ASTM C652	SW	HBA	>10,000	<6	<10	<10	<40
Smoky Mountain Williamsburg		Builders Special	ASTM C652	SW	HBA	>10,000	<6	<10	<10	<40
Stone City Williamsburg		Builders Special	ASTM C652	SW	HBA	>10,000	<6	<10	<10	<40
Tudor Williamsburg		Builders Special	ASTM C652	SW	HBA	>10,000	<6	<10	<10	<40
Wellington Williamsburg		Builders Special	ASTM C652	SW	HBA	>10,000	<6	<10	<10	<40

This data represents average results. If specific test results are required, sample should be taken from current production lots. U.S. STANDARD TEST METHODS (ASTM C67) ARE USED AS APPLICABLE, UNLESS OTHERWISE NOTED.

Size	Width	Height	Length	Weight	Brick per Cube	Brick per Sq Ft
Builders Special	3-1/8"	2-13/16"	8-5/8"	4.4	416	5.02