

# Technical Data Sheet

Woodsmoked Series

York Plant



Product Name	Swatch	Size	Standard	Durability Class (Grade)	Dimensional Variation (Type)	Compressive Strength (psi)	24-hr Cold Water Absorption (%)	5-hr Boil Absorption (%)	IRA (g/min per 30in <sup>2</sup> )	Core Volume (%)
Lorraine White		Handmade Oversize	ASTM C216	SW	TBA	>3,000	<14	<17	<48	uncored
Smokey Mountain		Handmade Oversize	ASTM C216	SW	TBA	>3,000	<14	<17	<48	uncored
Woodsmoked		Handmade Oversize	ASTM C216	SW	TBA	>3,000	<14	<17	<48	uncored

This data represents average results. If specific test results are required, sample should be taken from current production lots. U.S. STANDARD TEST METHODS (ASTM C67) ARE USED AS APPLICABLE, UNLESS OTHERWISE NOTED.

Size	Width	Height	Length	Weight	Brick per Cube	Brick per Sq Ft
Handmade Oversize	4"	2-3/4"	8-1/2"	6.4	385	5.2

Note: products are also available as Thin Brick, see Thin Brick Technical Data Sheet.

# Technical Data Sheet

Woodsmoked Series -- Thin Brick

York Plant



Product Name	Swatch	Size	Standard	Durability Class (Grade)	Dimensional Variation (Type)	Compressive Strength (psi)	24-hr Cold Water Absorption (%)	5-hr Boil Absorption (%)	IRA (g/min per 30in <sup>2</sup> )	Core Volume (%)
Lorraine White Thin Brick		Handmade Oversize	ASTM C1088	Exterior	TBA	N/A	<14	<17	N/A	N/A
Smokey Mountain Thin Brick		Handmade Oversize	ASTM C1088	Exterior	TBA	N/A	<14	<17	N/A	N/A
Woodsmoked Thin Brick		Handmade Oversize	ASTM C1088	Exterior	TBA	N/A	<14	<17	N/A	N/A

This data represents average results. If specific test results are required, sample should be taken from current production lots. U.S. STANDARD TEST METHODS (ASTM C67) ARE USED AS APPLICABLE, UNLESS OTHERWISE NOTED.

Size	Thickness	Width	Height	Length	Weight	Brick per Pack	Brick per Sq Ft
HMOS Thin Brick Flat	1"	1"	2-3/4"	8-1/2"	1.7	22	5.2
HMOS Thin Brick Corner	1"	4"	2-3/4"	8-1/2"	2.2	8	3.7/LF

Note: products are also available as Full Brick, see Full Brick Technical Data Sheet.