

# Technical Data Sheet

Downtown Series

Iberia Plant



Product Name	Swatch	Size	Standard	Durability Class (Grade)	Dimensional Variation (Type)	Compressive Strength (psi)	24-hr Cold Water Absorption (%)	5-hr Boil Absorption (%)	IRA (g/min per 30in <sup>2</sup> )	Core Volume (%)
Apple Creek		Modular	ASTM C216	SW	FBS	>5,000	<6	<10	<20	<25
		Utility	ASTM C216	SW	FBS	>5,000	<6	<10	<20	<25
Attica		Modular	ASTM C216	SW	FBS	>5,000	<6	<10	<20	<25
		Utility	ASTM C216	SW	FBS	>5,000	<6	<10	<20	<25
		Titan	ASTM C216	SW	FBS	>5,000	<6	<10	<20	<25
		Titan Plus	ASTM C652	SW	HBS				data to come	
Iberia Black		Modular	ASTM C216	SW	FBS	>5,000	<6	<10	<10	<25
		Utility	ASTM C216	SW	FBS	>5,000	<6	<10	<10	<25
		Titan	ASTM C216	SW	FBS	>5,000	<6	<10	<10	<25
		Titan Plus	ASTM C652	SW	HBS				data to come	
Ridgeland		Modular	ASTM C216	SW	FBS	>5,000	<6	<10	<20	<25
		Utility	ASTM C216	SW	FBS	>5,000	<6	<10	<20	<25
		Titan	ASTM C216	SW	FBS	>5,000	<6	<10	<20	<25
		Titan Plus	ASTM C652	SW	HBS				data to come	
Rockford		Modular	ASTM C216	SW	FBS	>5,000	<6	<10	<20	<25
		Utility	ASTM C216	SW	FBS	>5,000	<6	<10	<20	<25
Woodbury		Modular	ASTM C216	SW	FBS	>5,000	<6	<10	<20	<25
		Utility	ASTM C216	SW	FBS	>5,000	<6	<10	<20	<25

This data represents average results. If specific test results are required, sample should be taken from current production lots. U.S. STANDARD TEST METHODS (ASTM C67) ARE USED AS APPLICABLE, UNLESS OTHERWISE NOTED.

Size	Width	Height	Length	Weight	Brick per Cube	Brick per Sq Ft
Modular	3-9/16"	2-1/4"	7-5/8"	4.1	525	6.86
Utility	3-1/2"	3-5/8"	11-5/8"	9.6	198	3.00
Titan	3-1/2"	3-5/8"	15-5/8"	12.2	132	2.25
Titan Plus	7-1/2"	3-5/8"	15-5/8"	22.0	64	2.25