

TEST REPORT

Results of Tests on brick Conducted in accordance with ASTM C67/C67M-18 Standard Test Methods for Sampling and Testing Brick and Structural Clay Tile
04/01/2020

Name:	Glen-Gery Technical Services 433 South Pottsville Pike Shoemakersville, PA, 19555-0340	Plant:	Hanley Plant
Phone:	(p) (610) 562-3076	Sampled Date:	03/24/2020
Report Number:	GGHN97	Fired Date:	12/19/2020
Description:	Clay/Shale w/Additives Extruded Thin Brick		

Absorption	1	2	3	4	5	Average
<i>24 Hour Cold Water (%)</i>	2.7	2.7	2.6	2.6	2.8	2.7
<i>5 Hour Boiling Water (%)</i>	3.4	3.5	3.3	3.3	3.5	3.4
<i>Saturation Coefficient</i>	0.79	0.78	0.79	0.79	0.79	0.79

Efflorescence	1	2	3	4	5
<i>Efflorescence Detection</i>	Not Effloresced	Not Effloresced	Not Effloresced	Not Effloresced	Not Effloresced

The brick represented by the test results shown here comply with the physical property requirements of the standards listed below:

C1088-20 Standard Specification for Thin Veneer Brick Units Made From Clay or Shale
Grade: Exterior - Interior



Mike Krzyzanowski
Technical Services Manager