

## TEST REPORT

*Results of Tests on brick Conducted in accordance with ASTM C67/C67M-18 Standard Test Methods for Sampling and Testing Brick and Structural Clay Tile*  
12/02/2021

Name:	Glen-Gery Technical Services 433 South Pottsville Pike Shoemakersville, PA, 19555-0340	Plant:	Mid-Atlantic Plant
		Sampled Date:	11/12/2021
Phone:	(p) (610) 562-3076	Fired Date:	11/05/2021
Report Number:	GMAP569		
Description:	<b>Shale Molded Cut Thin Brick</b>		

<b>Absorption</b>	<b>1</b>	<b>2</b>	<b>3</b>	<b>4</b>	<b>5</b>	<b>Average</b>
<i>24 Hour Cold Water (%)</i>	4.5	4.1	3.7	3.4	4	3.9
<i>5 Hour Boiling Water (%)</i>	8.4	7.9	7.4	7.2	7.9	7.8
<i>Saturation Coefficient</i>	0.54	0.52	0.51	0.47	0.51	0.51
<b>Efflorescence</b>	<b>1</b>	<b>2</b>	<b>3</b>	<b>4</b>	<b>5</b>	
<i>Efflorescence Detection</i>	Not Effloresced	Not Effloresced	Not Effloresced	Not Effloresced	Not Effloresced	Not Effloresced

**The brick represented by the test results shown here comply with the physical property requirements of the standards listed below:**

C1088-20 Standard Specification for Thin Veneer Brick Units Made From Clay or Shale  
Grade: Exterior - Interior



Mike Krzyzanowski  
Technical Services Manager