

## TEST REPORT

*Results of Tests on brick Conducted in accordance with ASTM C67/C67M-18 Standard Test Methods for Sampling and Testing Brick and Structural Clay Tile*  
03/05/2020

Name:	Glen-Gery Technical Services 433 South Pottsville Pike Shoemakersville, PA, 19555-0340	Plant:	Sergeant Bluff Plant
		Sampled Date:	02/24/2020
Phone:	(p) (610) 562-3076	Fired Date:	08/12/2020
Report Number:	GGSB-0006		
Description:	<b>Clay Cut Thin Brick</b>		

<b>Absorption</b>	<b>1</b>	<b>2</b>	<b>3</b>	<b>4</b>	<b>5</b>	<b>Average</b>
<i>24 Hour Cold Water (%)</i>	4.3	4.2	4.5	4.4	4	4.3
<i>5 Hour Boiling Water (%)</i>	4.8	4.8	5.1	4.9	4.5	4.8
<i>Saturation Coefficient</i>	0.9	0.86	0.88	0.89	0.9	0.89

  

<b>Efflorescence</b>	<b>1</b>	<b>2</b>	<b>3</b>	<b>4</b>	<b>5</b>
<i>Efflorescence Detection</i>	Not Effloresced	Not Effloresced	Not Effloresced	Not Effloresced	Not Effloresced

**The brick represented by the test results shown here comply with the physical property requirements of the standards listed below:**

C1088-20 Standard Specification for Thin Veneer Brick Units Made From Clay or Shale  
Grade: Exterior - Interior



Mike Krzyzanowski  
Technical Services Manager