


Technical Data Sheet

Platinum Series
Hanley Plant



| Product Name | Swatch | Size | Standard | Durability Class (Grade) | Dimensional Variation (Type) | Compressive Strength (psi) | 24-hr Cold Water Absorption (%) | 5-hr Boil Absorption (%) | IRA (g/min per 30in ²) | Core Volume (%) |
|----------------------|---|---------|-----------|--------------------------|------------------------------|----------------------------|---------------------------------|--------------------------|------------------------------------|-----------------|
| Bone Velour |  | Modular | ASTM C216 | SW | FBX | >10,000 | <6 | <10 | <10 | <25 |
| Revere Pewter Velour |  | Modular | ASTM C216 | SW | FBX | >10,000 | <6 | <10 | <10 | <25 |
| Slate Velour |  | Modular | ASTM C216 | SW | FBX | >10,000 | <6 | <10 | <10 | <25 |
| White Velour |  | Modular | ASTM C216 | SW | FBX | >10,000 | <6 | <10 | <10 | <25 |

This data represents average results. If specific test results are required, sample should be taken from current production lots. U.S. STANDARD TEST METHODS (ASTM C67) ARE USED AS APPLICABLE, UNLESS OTHERWISE NOTED.

| Size | Width | Height | Length | Weight | Brick per Cube | Brick per Sq Ft |
|---------|--------|--------|---------|--------|----------------|-----------------|
| Modular | 3-5/8" | 2-1/4" | 7-5/8" | 4.0 | 525 | 6.86 |
| Utility | 3-5/8" | 3-5/8" | 11-5/8" | 10.0 | 198 | 3.00 |