Technical Data Sheet

La Paloma Series

International (Spain)



Product Name	Swatch	Size	Standard	Durability Class (Grade)	Dimensional Variation (Type)	Compressive Strength (psi)	24-hr Cold Water Absorption (%)	5-hr Boil Absorption (%)	IRA (g/min per 30in²)	Core Volume (%)
Azul		Modular Cored	ASTM C216	SW	FBX	>10,000	<6	<10	<20	<25
Azul Solid		Modular Solid	ASTM C216	sw	FBX	>10,000	<6	<10	<20	uncored
Castellana		Modular Cored	ASTM C216	sw	FBX	>10,000	<8	<17	<10	<25
Romero		Modular Cored	ASTM C216	sw	FBX	>10,000	<6	<10	<20	<25

This data represents average results. If specific test results are required, sample should be taken from current production lots. U.S. STANDARD TEST METHODS (ASTM C67) ARE USED AS APPLICABLE, UNLESS OTHERWISE NOTED. ©2024

Size	Width	Height	Length	Weight	Brick per Cube	Brick per Sq Ft			
Modular Cored	3-5/8"	2-1/4"	7-5/8"	4.0	680	6.86			
Modular Solid	3-5/8"	2-1/4"	7-5/8"	5.0	510	6.86			
Note: products are also available as Thin Brick, see Thin Brick Technical Data Sheet.									

Technical Data Sheet

La Paloma Series -- Thin Brick

International (Spain)



Product Name	Swatch	Size	Standard	Durability Class (Grade)	Dimensional Variation (Type)	Compressive Strength (psi)	24-hr Cold Water Absorption (%)	5-hr Boil Absorption (%)	IRA (g/min per 30in²)	Core Volume (%)
Azul Thin Brick		Modular	ASTM C1088	Exterior	ТВХ	N/A	<6	<10	N/A	N/A
Castellana Thin Brick		Modular	ASTM C1088	Exterior	твх	N/A	<8	<17	N/A	N/A
Romero Thin Brick		Modular	ASTM C1088	Exterior	твх	N/A	<6	<10	N/A	N/A

This data represents average results. If specific test results are required, sample should be taken from current production lots. U.S. STANDARD TEST METHODS (ASTM C67) ARE USED AS APPLICABLE, UNLESS OTHERWISE NOTED. ©2024

Size	Thickness	Width	Height	Length	Weight	Brick per Pallet	Brick per Sq Ft		
Modular Thin Brick Flat	3/4"	3/4"	2-1/4"	7-5/8"	1.0	2880	6.86		
Modular Thin Brick Corner	3/4"	3-5/8"	2-1/4"	7-5/8"	1.4	1800	4.5/LF		
Note: products are also available as Full Brick, see Full Brick Technical Data Sheet.									