Technical Data Sheet

Restore Series

Mid-Atlantic Plant



Product Name	Swatch	Size	Standard	Durability Class (Grade)	Dimensional Variation (Type)	Compressive Strength (psi)	24-hr Cold Water Absorption (%)	5-hr Boil Absorption (%)	IRA (g/min per 30in ²)	Core Volume (%)
160-M		Modular	ASTM C216	sw	FBS	>5,000	<8	<10	<30	<25
		Engineer Modular	ASTM C216	sw	FBS	>5,000	<8	<10	<30	<25
192-M		Modular	ASTM C216	sw	FBS	>5,000	<8	<10	<30	<25
		Engineer Modular	ASTM C216	sw	FBS	>5,000	<8	<10	<30	<25
Bradford		Modular	ASTM C216	SW	FBS	>5,000	<8	<10	<30	<25
		Engineer Modular	ASTM C216	sw	FBS	>5,000	<8	<10	<30	<25

This data represents average results. If specific test results are required, sample should be taken from current production lots. U.S. STANDARD TEST METHODS (ASTM C67) ARE USED AS APPLICABLE, UNLESS OTHERWISE NOTED. ©2024

Size	Width	Height	Length	Weight	Brick per Cube	Brick per Sq Ft			
Modular	3-5/8"	2-1/4"	7-5/8"	4.3	530	6.86			
Engineer Modular	3-5/8"	2-3/4"	7-5/8"	5.4	430	5.76			
Note: Products are also available as Thin Brick, see Thin Brick Technical Data Sheet.									

Technical Data Sheet

Restore Series -- Thin Brick Mid-Atlantic Plant



	Product Name	Swatch	Size	Standard	Durability Class (Grade)	Dimensional Variation (Type)	Compressive Strength (psi)	24-hr Cold Water Absorption (%)	5-hr Boil Absorption (%)	IRA (g/min per 30in²)	Core Volume (%)
16	60-M Thin Brick		Modular	ASTM C1088	Exterior	TBS	N/A	<8	<10	N/A	N/A
19	2-M Thin Brick		Modular	ASTM C1088	Exterior	твѕ	N/A	<8	<10	N/A	N/A
Bra	dford Thin Brick	计片	Modular	ASTM C1088	Exterior	твѕ	N/A	<8	<10	N/A	N/A

This data represents average results. If specific test results are required, sample should be taken from current production lots. U.S. STANDARD TEST METHODS (ASTM C67) ARE USED AS APPLICABLE, UNLESS OTHERWISE NOTED. ©2024

Size	Thickness	Width	Height	Length	Weight	Brick per	Brick per	Brick per Sq		
3126	HIICKHESS	wiatii				Pack	Pallet	Ft		
Modular Thin Brick Flat	3/4"	3/4"	2-1/4"	7-5/8"	1.1	30	2700	6.86		
Modular Thin Brick Corner	3/4"	3-5/8"	2-3/4"	7-5/8"	1.4	12	1080	4.5/LF		
Note: Products are also available as Full Brick, see Full Brick Technical Data Sheet.										