




Mid-Atlantic Plant



Product Name	Swatch	Size	Standard	Durability Class (Grade)	Dimensional Variation (Type)	Compressive Strength (psi)	24-hr Cold Water Absorption (%)	5-hr Boil Absorption (%)	IRA (g/min per 30in ²)	Core Volume (%)
Olde City		Standard	ASTM C216	SW	FBA	>5,000	<6	<10	<30	<25
Olde England		Standard	ASTM C216	SW	FBA	>5,000	<6	<10	<30	<25
Olde London		Standard	ASTM C216	SW	FBA	>5,000	<6	<10	<30	<25

This data represents average results. If specific test results are required, sample should be taken from current production lots.
U.S. STANDARD TEST METHODS (ASTM C67) ARE USED AS APPLICABLE, UNLESS OTHERWISE NOTED. ©2025

Size	Width	Height	Length	Weight	Brick per Cube	Brick per Sq Ft
Extruded Standard	3-5/8"	2-1/4"	8"	4.6	530	6.55

Note: products are also available as Thin Brick, see Thin Brick Technical Data Sheet.