## **Technical Data Sheet**

## San Selmo Smoked Series

International (Italy)



| Product Name | Swatch | Size     | Standard  | Durability<br>Class<br>(Grade) | Dimensional<br>Variation<br>(Type) | Compressive<br>Strength<br>(psi) | 24-hr Cold<br>Water<br>Absorption<br>(%) | 5-hr Boil<br>Absorption<br>(%) | IRA<br>(g/min per<br>30in <sup>2</sup> ) | Core Volume<br>(%) |
|--------------|--------|----------|-----------|--------------------------------|------------------------------------|----------------------------------|--|--------------------------------|--|--------------------|
| Arctic Ivory |        | Oversize | ASTM C216 | SW                             | FBA                                | >3,000                           |  | M 50-Cycle<br>aw Testing       | <53                                      | uncored            |
| Opaque Slate |        | Oversize | ASTM C216 | SW                             | FBA                                | >3,000                           |  | M 50-Cycle<br>aw Testing       | <30                                      | uncored            |

This data represents average results. If specific test results are required, sample should be taken from current production lots. U.S. STANDARD TEST METHODS (ASTM C67) ARE USED AS APPLICABLE, UNLESS OTHERWISE NOTED. ©2025

| Size     | Width | Height | Length | Weight | Brick per<br>Pallet | Brick per Sq<br>Ft |
|----------|-------|--------|--------|--------|---------------------|--------------------|
| Oversize | 4"    | 2-3/4" | 8-1/2" | 5.6    | 270                 | 5                  |