

Technical Data Sheet

San Selmo Corso Series
International (Italy)



Product Name	Swatch	Size	Standard	Durability Class (Grade)	Dimensional Variation (Type)	Compressive Strength (psi)	24-hr Cold Water Absorption (%)	5-hr Boil Absorption (%)	IRA (g/min per 30in ²)	Core Volume (%)
Adda Raw		Corso	ASTM C216	SW	FBA	>3,000	Passes ASTM 50-Cycle Freeze/Thaw Testing		<65	uncored
Arno Raw		Corso	ASTM C216	SW	FBA	>3,000	Passes ASTM 50-Cycle Freeze/Thaw Testing		<65	uncored
Brenta Raw		Corso	ASTM C216	SW	FBA	>3,000	Passes ASTM 50-Cycle Freeze/Thaw Testing		<65	uncored
Livenza Raw		Corso	ASTM C216	SW	FBA	>3,000	Passes ASTM 50-Cycle Freeze/Thaw Testing		<65	uncored
Piave Raw		Corso	ASTM C216	SW	FBA	>3,000	Passes ASTM 50-Cycle Freeze/Thaw Testing		<65	uncored
Potenza Raw		Corso	ASTM C216	SW	FBA	>3,000	Passes ASTM 50-Cycle Freeze/Thaw Testing		<65	uncored
Reno Raw		Corso	ASTM C216	SW	FBA	>3,000	Passes ASTM 50-Cycle Freeze/Thaw Testing		<65	uncored

This data represents average results. If specific test results are required, sample should be taken from current production lots. U.S. STANDARD TEST METHODS (ASTM C67) ARE USED AS APPLICABLE, UNLESS OTHERWISE NOTED. ©2024

Size	Width	Height	Length	Weight	Brick per Pallet	Brick per Sq Ft
Corso	3-15/16"	1-9/16"	19-11/16"	8.1	137	3.7

The maximum allowed warpage, as defined in ASTM C216 section 9, of Type FBA Corso units shall be ¼" (6.4mm).